

# BENCHMARK


## SELECT

### Technical Data Sheet | Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	68
Ultimate Stretch	FPT-750	Percent	380%
Puncture Force	FPT-750	lbf	5.76
Cling	FPT-750	Grams	110.7
Tear Force	FPT-750	lbf	22.8
Tear Time	FPT-750	Seconds	13.7

### BM Select 68 Ga :: Ultimate Test

● Recovery Force ● Stretch Force



**Recovery Force:** Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

**Stretch Force:** Is the amount of force required to stretch a film at a given stretch percentage, and relates to a films resistance to further stretch.

**20"x7,000'** Item #5122070  
 (800) 722-5841 | www.atlanticpkg.com

