

BENCHMARK

EXTREME


Technical Data Sheet | Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	80
Ultimate Stretch	FPT-750	Percent	450%
Puncture Force	FPT-750	lbf	10.3
Cling	FPT-750	Grams	118.8
Tear Force	FPT-750	lbf	25.4
Tear Time	FPT-750	Seconds	16.2

BM Extreme 80 Ga :: Ultimate Test

● Recovery Force

● Stretch Force



Recovery Force: Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

Stretch Force: Is the amount of force required to stretch a film at a given stretch percentage, and relates to a film's resistance to further stretch.

20" x 5,500' Item #5622055
 (800) 722-5841 | www.atlanticpkg.com

