



ELEMENT


STRETCH FILM

Technical Data Sheet | Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	57
Ultimate Stretch	FPT-750	Percent	437%
Puncture Force	FPT-750	lbf	9.1
Cling	FPT-750	Grams	123
Tear Force	FPT-750	lbf	22.3
Tear Time	FPT-750	Seconds	15.8

BM Element Ga 57 :: Ultimate Test

● Recovery Force ● Stretch Force



Recovery Force: Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

Stretch Force: Is the amount of force required to stretch a film at a given stretch percentage, and relates to a film's resistance to further stretch.