




Technical Data Sheet | Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	60
Ultimate Stretch	FPT-750	Percent	410%
Puncture Force	FPT-750	lbf	9.7
Cling	FPT-750	Grams	141
Tear Force	FPT-750	lbf	21.4
Tear Time	FPT-750	Seconds	10.0

BM BB Gold XL 60 Ga :: Ultimate Test

● Recovery Force ● Stretch Force



Recovery Force: Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

Stretch Force: Is the amount of force required to stretch a film at a given stretch percentage, and relates to a film's resistance to further stretch.

20"x7,250' Item #5612249
 (800) 722-5841 | www.atlanticpkg.com

