




# HDC BLACK

## STRETCH FILM

### Technical Data Sheet | Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	150
Ultimate Stretch	FPT-750	Percent	433%
Puncture Force	FPT-750	lbf	7.7
Cling	FPT-750	Grams	214
Tear Force	FPT-750	lbf	57.7
Tear Time	FPT-750	Seconds	24.1

### BM HDC-Black 150 Ga :: Ultimate Test ● Recovery Force ● Stretch Force



**Recovery Force:** Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

**Stretch Force:** Is the amount of force required to stretch a film at a given stretch percentage, and relates to a film's resistance to further stretch.