



# HDC

## STRETCH FILM


### Technical Data Sheet | Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	63
Ultimate Stretch	FPT-750	Percent	360%
Puncture Force	FPT-750	lbf	4.6
Cling	FPT-750	Grams	125
Tear Force	FPT-750	lbf	18.8
Tear Time	FPT-750	Seconds	7.9

### BM HDC M 63 Ga :: Ultimate Test

● Recovery Force

● Stretch Force



**Recovery Force:** Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

**Stretch Force:** Is the amount of force required to stretch a film at a given stretch percentage, and relates to a film's resistance to further stretch.

**20"x5000'** Item #6181221  
 (800) 722-5841 | www.atlanticpkg.com

