




Technical Data Sheet | Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	51
Ultimate Stretch	FPT-750	Percent	360%
Puncture Force	FPT-750	lbf	6.3
Cling	FPT-750	Grams	121
Tear Force	FPT-750	lbf	19.7
Tear Time	FPT-750	Seconds	6.4

BM BB Performance XL 51 Ga :: Ultimate Test

● Recovery Force ● Stretch Force



Recovery Force: Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

Stretch Force: Is the amount of force required to stretch a film at a given stretch percentage, and relates to a film's resistance to further stretch.