

SLIP/ MAX


STRETCH FILM

Representative Data:

Properties	Method	Units	Value
Thickness	Atlantic	Gauge	61
Ultimate Stretch	FPT-750	Percent	403%
Puncture Force	FPT-750	lbf	9.3
Cling	FPT-750	Grams	174
Tear Force	FPT-750	lbf	20.6
Tear Time	FPT-750	Seconds	12.7

BM SlipMax20 61 Ga :: Ultimate Test

● Recovery Force ● Stretch Force



Recovery Force: Is indicative of the amount of compressive force a given film will exert on a unit load when applied at the listed strain conditions.

Stretch Force: Is the amount of force required to stretch a film at a given stretch percentage, and relates to a film's resistance to further stretch.