



Benchmark Global Gold

TYPICAL APPLICATIONS:

For manual or automatic case and carton sealing.
Recommended for medium weight cartons in general shipping and manufacturing environments.

FILM BACKING:

Biaxially oriented polypropylene.

ADHESIVE:

Pressure sensitive; Hot melt rubber resin.

TYPICAL VALUES:

	Standard	Metric
Thickness	1.8 mils	.05 mm
Tensile Strength (Longitudinal Direction)	25 lbs / lbs in width	43.8N / 10mm width
Elongation	145%	145%
Adhesion to Stainless Steel	40 oz / in width	4.38N / 10mm width
Adhesion to Backing		
Holding Power to Fiberboard	10,000 minutes +	
Application Temperature Range	35F to 110F	2C to 43C
Service Temperature Range	-20F to 150F	-29C to 66C

AVAILABLE SIZES:

Standard Widths: 48 mm, 72 mm
Core Size (ID): 3 in.
Standard Lengths: 100 m, 914 m, 1500 m

STORAGE & USAGE CONDITIONS:

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.